



profile kwadratowe

wymiar (A=B)		grubość								
A mm	B mm	1	1,2	1,5	2	2,5	3	4	5	6
12	12	0,358								
15	15	0,453	0,538	0,661						
16	16	0,485	0,576	0,709						
19	19	0,567	0,675	0,832	1,090					
20	20	0,613	0,729	0,901	1,176					
22	22	0,677	0,806	0,996	1,303					
25	25	0,772	0,921	1,140	1,495	1,837	2,167			
30	30	0,932	1,112	1,379	1,814	2,236	2,645			
32	32	0,960	1,150	1,420	1,870	2,310	2,740			
35	35	1,091	1,304	1,618	2,133	2,635	3,124			
40	40	1,251	1,495	1,858	2,452	3,033	3,602	4,703		
45	45	1,410	1,686	2,097	2,771	3,432	4,081			
50	50		1,878	2,336	3,090	3,831	4,559	5,979	7,349	
60	60			2,814	3,728	4,628	5,516	7,255	8,943	
70	70			3,293	4,366	5,426	6,473	8,531	10,538	
80	80			3,771	5,004	6,223	7,430	9,807	12,133	14,410
100	100			4,728	6,279	7,818	9,344	12,359	15,323	18,237
120	120				7,555	9,413	11,258	14,910	18,513	22,065
140	140				8,831	11,008	13,172	17,462	21,703	25,893
150	150				9,469	11,805	14,129	18,738	23,298	27,807
200	200				12,659	15,793	18,913	25,118	31,272	37,376

profile kwadratowe

wymiar (A=B)		grubość mm					
A mm	B mm	1,24	1,65	2,11	2,77	3,05	4,57
		waga kg/m					
12,7	12,7	0,464	0,600	0,743			
15,88	15,88	0,590	0,768	0,957			
19,05	19,05	0,715	0,934	1,171	1,491	1,620	
25,4	25,4	0,966	1,269	1,598	2,052	2,238	
31,75	31,75	1,217	1,603	2,025	2,613	2,856	
38,1	38,1	1,468	1,937	2,453	3,174	3,474	
44,45	44,45	1,720	2,271	2,880	3,735	4,092	
50,8	50,8	1,971	2,606	3,308	4,296	4,709	6,882
63,5	63,5	2,473	3,274	4,162	5,419	5,945	8,734
76,2	76,2	2,975	3,942	5,017	6,541	7,181	10,585
101,6	101,6	3,980	5,279	6,727	8,785	9,652	14,288

Podany zakres obejmuje część wymiarów